

FRANZ HOFFMANN - FEINLEDER

Export – Import / Inh. Th. Schmidt e.K.

Schwabstr. 36B / DE 70197 Stuttgart

Telefon: ++49 (0) 711- 61 74 75 Fax: ++49 (0) 711- 615 95 38

E-Mail: info@feinleder-hoffmann.com**TECHNICAL CHARACTERISTIC OF CNI/CNIN**

Test Method	Property	Requirements	Average values of CNI
UNI ISO 3376	Determination of tensile strength	<ul style="list-style-type: none">• $\geq 6 \text{ N/mm}^2$	- Along. 12.4 N/mm^2 - Across. 10.8 N/mm^2
UNI ISO 3376	Determination of elongation	<ul style="list-style-type: none">• $> 20 \%$	- Along. 30% - Across. 44%
UNI 4914	Determination of tear strength	<ul style="list-style-type: none">• $\geq 3 \text{ N/mm}^2$	- Along. 7.2 N/mm^2 - Across. 8.6 N/mm^2
UNI EN 12772	Determination of dimension stability	<ul style="list-style-type: none">• $\leq 2 \%$	$< 2 \%$

Reconstituted Leather from vegetal tanned leather only.
Material produced by automatic continuous system.

FRANZ HOFFMANN - FEINLEDER

Export – Import / Inh. Th. Schmidt e.K.

Schwabstr. 36B / DE 70197 Stuttgart

Telefon: ++49 (0) 711- 61 74 75 Fax: ++49 (0) 711- 615 95 38

E-Mail: info@feinleder-hoffmann.com

CNI/CNIN

Vegetable tanned leather	60%
Bonding agent (natural latex)	24%
Products tanned and water	16%
Density (average)	0.90 ± 0.5
Usual commercial size	Rolls size: length m 50- width cm 150 abt. Sheets size: cm 100x150 abt.
Standard thickness available	from 0.4 mm to 1.8 mm
Tolerance on thickness	± 0.1 mm

MATERIAL IN CONFORMITY WITH REACH LEGISLATION.

The exclusive presence of leather scraps only vegetal tanned and the quantity conformity of chemical substance as Chrome VI, Pentachorophenol, Azocolorants, Aromatic Ammins and Clorurate Substance, makes the material in accordance to Italian and Europeans rules for toxicity.